

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 October 2003 (16.10.2003)

PCT

(10) International Publication Number
WO 03/086029 A1

(51) International Patent Classification?: **H05H 1/24**

(21) International Application Number: PCT/EP03/04344

(22) International Filing Date: 8 April 2003 (08.04.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0208263.4 10 April 2002 (10.04.2002) GB

(71) Applicants (for all designated States except US): **DOW CORNING IRELAND LIMITED** [IE/IE]; Unit 12, Owenacurra Business Park, Midleton, Co Cork (IE). **DOW CORNING CORPORATION** [US/US]; Midland, MI 48611 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **GOODWIN, Andrew, James** [GB/IE]; Melrose, Moneygourney, Douglas,

Co Cork (IE). **LEADLEY, Stuart** [GB/IE]; 30 Lauriston, The Park, Midleton, Co Cork (IE). **CHEVALIER, Pierre** [FR/GB]; 5 Plymouth Road, Penarth CF64 3DA (GB). **PARBHOO, Bhukandas** [BE/GB]; Suraj, Weston Avenue, Sully, Penarth CF64 5SW (GB).


(74) Agents: **DONLAN, Andrew, M.** et al.; Dow Corning Limited, Cardiff Road, Barry CF63 2YL (GB).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: GEL AND POWDER MAKING



(57) Abstract: A method of forming a gel and/or powder of a metallic oxide, metalloid oxide and/or a mixed oxide or resin thereof from one or more respective organometallic liquid precursors(s) and/or organometaloid liquid precursors(s) by oxidatively treating said liquid in a non-thermal equilibrium plasma discharge and/or an ionized gas stream resulting therefrom and collecting the resulting product. The non-thermal equilibrium plasma is preferably atmospheric plasma glow discharge, continuous low pressure glow discharge plasma, low pressure pulse plasma or direct barrier discharge. The metallic oxides this invention particularly relates to are those in columns 3a and 4a of the periodic table namely, aluminium, gallium, indium, tin and lead and the transition metals. The metalloids may be selected from boron, silicon, germanium, arsenic, antimony and tellurium. Preferred metalloid oxide products made according to the process of the present invention are in particular oxides of silicon including silicone resins and the like, boron, antimony and germanium.

WO 03/086029 A1